

Coadd™ AT-2893

Corrosion Inhibitor

DESCRIPTION

Coadd™ AT-2893 is a solution of unsaturated polyacid amide, and is suitable for both water-borne and solvent-borne coating systems. The product can improve the salt-spray resistance and water resistance of the metal coatings.

PHYSICAL PROPERTIES

Appearance	Yellowish liquid
Density (g/ml)	0.99
Active content (%)	30-35
Viscosity (25℃, mPas)	<500

Note: These properties are only typical, and do not represent product specifications

APPLICATION CHARACTERISTIC AND ADVANTAGES

Coadd™ AT-2893 is recommended for both water-borne and solvent borne coating systems, especially effective in metal coatings to improve the salt-spray resistance and water resistance. For water-borne system, please dilute with coalescent (such as: Texanol, DPNB, BCS, DPM) in ratio 1:1 to 2:1, then add it in let-down stage. For solvent-borne system, can be added directly, or dilute in the ratio above mentioned with solvent which used in formulations.

Suggested dosage (base on the total formulation weight): 0.5-2.0%.

The above recommended dosage is only for orientation, optimal level of dosage should be determined via laboratory tests.

SAFETY NOTICE

Before using the products, please refer to SDS for detailed safety data, handling and storage procedures recommended.

DISCLAIMER

It is common proposal for product usage and demand above information based on our professional knowledge. Due to environmental uncertainty and out of our control from practical process, please test and make evaluation ahead of use to ensure efficient and safe. For your reference, the above information is only for commonly known and use the product. It is guaranteed to meet quality and product specification.

****Please refer to SDS for more information**